

PVA natur

- Temperature print: 200-230°C for 2,90 mm filament / 195-225 °C for 1,75 mm filament
- Temperature pad: about 40°C

Material data sheet for PVA natur:

Melt flow rate [g/10 min]	Melting temp. [°C]	Glass trans. temp. [°C]	Bulk density [g/cm ³]	Volatile content [w%]	Methanol content [w%]	Solubility
14-20 (190°C, 21,6kg)	163	62	0,6-0,9	1 (0,2)	< 1	cold