

Technical Data Sheet



Product name: Volcano PLA

Version: v3

Volcano PLA is an industrial grade PLA which is engineered for professional applications that require high printing speeds and improved heat resistance and mechanical properties similar to ABS.

Volcano PLA offers the same mechanical and thermal properties - after annealing - as most ABS filaments, but with the biodegradability and ease of printing of PLA. Volcano PLA combines a high heat resistance with high printing speeds and high impact resistance into a PLA-based filament engineered for industrial applications.

Properties	Typical value	Test Method	Test condition
Physical			
Specific gravity	1.27 g/cc	ASTM D792	-
Melt flow rate	6 g/10 min*	ISO 1133	210° C/2.16Kg
<i>* Higher melt flow rate at a higher printing temperature (240°C ±10°C), which increases the printing speed capabilities.</i>			
Mechanical			
Impact strength	22 KJ/m ²	ISO 179	Charpy Notched @23° C (73° F)
Tensile strength	39 Mpa	ISO 527	-
Tensile modulus	3900 Mpa	ISO 527	-
Elongation at break	58%	ISO 527	-
Flexural strength	-	-	-
Flexural modulus	-	-	-
Hardness	-	-	-
Thermal			
Print temperature	± 220 - 255° C	-	-
Melting temperature	± 190 - 220° C	-	-
Viscat softening temp.	≥ 95° C After annealing	ISO 75	-
Optical			
Haze	-	-	-
Transmittance	-	-	-
Gloss	-	-	-

Product details, certifications and compliance	Diameter	Tolerance	Roundness
HS Code	39169090	1.75mm ± 0.05mm	≥ 95%
REACH compliant	Yes	2.85mm ± 0.10mm	≥ 95%
RoHS certified	Yes		

Formfutura BV	CoC: 69099502	Tel: +31 (0)85 002 0881
Groenestraat 215	VAT: NL857733709B01	Email: info@formfutura.com
6531 HH Nijmegen	EORI: NL857733709	Website: www.formfutura.com
The Netherlands		

All information supplied by or on behalf of Formfutura in relation to its products, whether in the nature of data, recommendations or otherwise, is supported by research and, in good faith, believed reliable, but Formfutura assumes no liability and makes no warranties of any kind, express or implied, including, but not limited to, those of title, merchantability, fitness for a particular purpose or non-infringement or any warranty arising from a course of dealing, usage, or trade practice whatsoever in respect of application, processing or use made of the forementioned information or product. The user assumes all responsibility for the use of all information provided and shall verify quality and other properties or any consequence from the use of all such information. Typical values are indicative only and are not to be construed as being binding specifications.